

## Technical Data Sheet

### Olive Green Passivation EB-404

Olive green Passivation EB-404 is an ambient temperature immersion process for producing leaf-green conversion coating on alkaline zinc, acid zinc and cyanide zinc plated surfaces. Green passivation offer good corrosion resistance. One hundred fifty plus SST hours (white rust) can be achieved.

#### Make-Up Method:-

- Firstly clean tank thoroughly (PP, PVC Tank Recommended).
- Add required quantity of EB-404 with gentle stir.
- Maintain Operating level of tank with distilled water and mix well.
- Check and adjust pH with 50% Nitric acid to lower ph., add 50% sodium hydroxide to raise pH

#### Operating Parameters:-

- Temperature:- Ambient Temperature
- Concentration:- 80~120ml/litter (Optimum 100ml/litter)
- Residence Time:- 30-60 second`s
- pH:- 1.2~2.0

#### Process:-

- Zinc Plating (10~12 micron recommended)
- Water rinse
- Water rinse
- Nitric Acid dip 0.4%
- Water rinse
- Green Passivation EB-404
- Water rinse
- Water rinse
- Hot Dry (50~60 °c)

#### Replenishment:-

Bath is replenished by visual observation or by analysis. Small additions of EB-404 are added to the bath with stirring normally 0.8 to 1 liters of passivation EB-404 will consumed work treatment of one seventy five square feet's

#### Cautions:

- Must Wear PPE's Rubber Gloves, Long shoes and apron during chemicals mixing.
- Care should be taken while adding nitric acid.

#### Waste Treatment:

Olive Green Passivation EB-404 solutions contains chromic acid (hexavalent). It should be neutralized with ferrous sulfate to trivalent stage and upon reduction should be neutralized with alkali before discarding into sewerage line.